

MATERIAL	WEIGHT	THICKNESS	BREAKING STRENGTH				BREAKING ELONGATION		STATIC PUNCH (CBR)
			MD		CD		(%)		N
	(gr/m2)	(mm)	kN/m	N/5cm	kN/m	N/5cm	MD	CD	
White 150	150	1,4	1,80	90	2,20	110	40-60	40-55	320
White 200	200	1,8	2,00	100	2,40	120	40-60	40-55	475
White 250	250	2,3	3,00	150	4,40	220	40-60	40-55	750
White 300	300	2,9	4,00	200	5,60	280	40-60	40-55	800
White 400	400	3,8	5,10	255	7,00	350	40-60	40-55	910
White 500	500	4,7	6,20	310	9,00	450	40-60	40-55	1530

MATERIAL	WEIGHT	THICKNESS	BREAKING STRENGTH				BREAKING ELONGATION		STATIC PUNCH (CBR)
			MD		CD		(%)		N
	(gr/m2)	(mm)	kN/m	N/5cm	kN/m	N/5cm	MD	CD	
Grey 150	150	1,41	2,20	110	2,50	125	45-65	30-50	155
Grey 200	200	2,42	2,50	125	3,20	160	45-65	30-50	260
Grey 250	250	2,58	2,60	130	3,90	195	45-65	30-50	365
Grey 300	300	3,21	2,70	135	5,00	250	45-65	30-50	500
Grey 400	400	4,2	3,30	165	5,60	280	45-65	30-50	875
Grey 500	500	4,3	4,20	210	7,00	350	45-65	30-50	1645

**NOTE:** Measured values are made in their laboratory Sankılıç textile may differ outside the measured value  $\pm 10\%$  .

Necip Fazıl Mah. Yaver Sk. ALK Plaza No:1 D:8

Ümraniye - İSTANBUL

Tel : +90 216 339 12 12 Fax : +90 216 339 12 17

www.nanotekgrup.com