

**Chemical resistance of MasterTop TC 941**

| Chemicals                        | MasterTop TC 941 |
|----------------------------------|------------------|
| Acetone                          | (+)              |
| Acetic acid 5 %                  | –                |
| Ammonia up to 32 %               | +                |
| Brake fluid                      | +                |
| Butanol                          | (+)              |
| Calcium hydroxide saturated      | (+)              |
| Caustic soda solution up to 10 % | +                |
| Caustic soda solution 50 %       | –                |
| Citric acid 10 %                 | +                |
| Diesel fuel                      | +                |
| Engine oil                       | (+)              |
| Ethanol                          | +                |
| Ethyl acetate                    | +                |
| Formic acid 2 %                  | –                |
| Formic acid 5 %                  | –                |
| Fruit juice                      | +                |
| Heating oil                      | +                |
| Hydrochloric acid 20%            | –                |
| Hydraulic fluid                  | +                |
| Hydrogen peroxide 30 %           | –                |
| Jet fuel                         | +                |
| Lactic acid 10 %                 | –                |

**Chemical resistance of MasterTop TC 941**

| Chemicals                               | MasterTop TC 941 |
|---|------------------|
| Methanol                                | (+)              |
| Methylene chloride                      | –                |
| Methyl ethyl ketone (MEK)               | –                |
| Nitric acid 10 %                        | –                |
| Nitric acid 20 %                        | –                |
| Phosphoric acid 20 %                    | –                |
| Potassium hydroxide solution up to 50 % | (+)              |
| Propanol                                | +                |
| Skydrol                                 | +                |
| Sodium carbonate, saturated             | +                |
| Sodium chloride solution, any           | +                |
| Sodium sulphate solution, any           | +                |
| Sugar                                   | +                |
| Sulphuric acid 50 %                     | –                |
| Transmission fluid                      | +                |
| Vegetable oils                          | +                |
| Water                                   | +                |
| Xylene                                  | (+)              |

+

resistant for 28 days

(+)

resistant for 3 days

–

not resistant

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.