

MasterCrete™ N 600 (Yapkret® T)

Non-structural Repair Mortar

Material Description

MasterCrete™ N 600 is cement based one part, polymer modified repair mortar for nonstructural repairs on concrete structures.

Complies with EN 1504-3/R1

Areas of Application

- Repairing and reprofiling the concrete surfaces,
- Repairing and plastering the exposed concrete,
- Repairing and plastering the slabs and ceilings,
- Repair of the defects on the concrete surfaces before coating (tile etc.) applications.

Characteristics and Benefits

- Mixed with only water and can be applied easily
- Provides smooth surfaces
- Perfect bonding to the concrete substrates
- Can be applied in wide areas without cracking
- Provides high thixotropic properties

Processing Method

(A) Preparation of Substrate

The concrete surfaces must be sound, clean and dry. It shouldn't be weakened by over-troweling and lack of curing. The concrete should be free of frost, curing membranes, waterproofing treatments, oil stains,

laitance, friable material and dust. If there is a water leakage it must be drained or properly plugged. Defects up to 4 cm depth should be repaired with **MasterCrete™ S88 C** before starting to **MasterCrete™ N 600** applications. Concrete surfaces must be saturated with water before application.

(B) Mixing

Add enough water into a clean mixing bucket by using a proper water gauge. Add the powder into the bucket slowly and continuously. Mix the fresh mortar with a proper electrical mixer (300-600 rpm) for 4 minutes until having a homogenous consistency. Let the mortar have rest for 4 minutes and re-mix for 30 seconds.


Mixing Ratio

MasterCrete™ N 600	Amount of Mixture Water	Density of Mixture
For 1 kg Powder	0,225 liter	1,90
For 20 kg Bag	4,50 liter	kg/liter

(C) Processing

MasterCrete™ N 600 should be applied to the prepared surface by using a steel trowel. Application thickness should be between 5-30 mm. After the mortar finishes its first setting, some water should be

Technical Properties

Structure of the Material	Mineral Fillers, Fibre and Polymer Modified Cement	
Color	Grey	WK
Compressive Strength (TS EN 196) (28 days)	>10 N/mm ²	
Bonding Strength to concrete (TS EN 1542) (28 days)	>1,0 N/mm ²	
Application Thickness	Min. 5 mm Max. 30 mm	
Application Temperature	+5°C + 30°C	
Pot Life (20°C)	30 minutes	
Fully Cured (20°C)	28 days	

Typical values are obtained from the test results of 4x4x16 mortar prism in 23°C and 50% relative humidity conditions. High temperatures shortens the curing and working time, lower temperatures extends the durations.

MasterCrete™ N 600 (Yapkret® T)

Non-structural Repair Mortar

sprayed onto the mortar and the surface should be finished with using steel or wooden trowel. Open areas should be protected from the rain, wind, etc. Aggressive whether conditions during the first 24-48 hours after finishing repair by using wet clothes, curing membranes etc.

Consumption

15.50 kg/m² for obtaining 10 mm thick layer.

Point to Consider

- Mixed mortar must be used in 30 minutes in 20°C. Working time will be 20 minutes in 30°C.
- Open areas should be protected from the rain, wind, etc. aggressive whether conditions during the first 24 hours after finishing repair.
- Cement based materials' pot life and curing times vary depending on the relative humidity, substrate and ambient temperature.
- Reaction gets slow in low temperatures and it causes to extension on pot life and working time. On the other hand high temperatures speed up the reaction, which results to short pot life and working time. For full curing of material, both the substrate and ambient temperature shouldn't be under allowed application temperature.

Cleaning of Tools

All the tools and equipments must be cleaned by water after the application. After **MasterCrete™ N 600** is hardened, it can only be removed from the surface mechanically.

Packaging

MasterCrete™ N 600 is available in 20 kg polyethylene reinforced kraft bag.

Shelf Life

12 months after the production date under appropriate storing conditions. Opened packages have to be stored by tightly sealing the bag/cover and must be used in one week.

Storage

Must be stored in unopened original packing, and in cool and dry environment protected from freezing. In short-term storing, maximum 3 palettes can be stowed on top of each other and delivery has to be according to first in first out system. In long-term storing, the palettes must not be stowed on top of each other.

Health and Safety

It is dangerous to approach the application sites. During the application, a protective apparel, protective gloves, goggles and masks which comply with the Occupational Health and Safety Rules should be used. Due to the irritation effect of the uncured materials, the mixture should not come into contact with skin and eyes; in case of a contact, the affected area should be washed with plenty of water and soap; in case of swallowing, a physician should be consulted immediately. No food or beverages should be brought to the application area. The product should be stored and kept out of reach of children. For detailed information please consult the Material Safety Data Sheet.

Disclaimer

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. **MBT Teknik Yapı Kimyasalları Sanayi ve Ticaret A.Ş.** is only responsible for the quality of the product **MBT Teknik Yapı Kimyasalları Sanayi ve Ticaret A.Ş.** is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is implemented and nullifies the old ones.

Contact

MBT Teknik Yapı Kimyasalları San. ve Tic. A.Ş.
Eyüp Sultan Mah. Sekmen Cad. Hayy 1000A
No:26/8 Sancaktepe, İstanbul
Tel: 0216 561 35 45 www.mbt-tech.tr