



DATA SHEET

PRODUCTION CODE : KR0180MD1001N012

NAME : KORUSER MAVI

RAW MATERIAL

TYPE OF FIBER

120 gr/m2 PES

TYPE OF CHEMICAL

30 gr/m2 BINDER+30gr/m2 BREATHABLE PE FILM

TESTS

METHOD

UNIT

CRITERIA OF ACCEPTANCE

MIN.

MAX.

TARGET

WEIGHT

TS EN 29073-1

g / m²

162

198

180

THICKNESS

TS EN 9073-2

mm

1

-

-

WIDTH

TL.013

cm

99

101

100

APPEARANCE

TL.014

STD.SAMP.

STD.SAMP.

STD.SAMP.

TENSILE STRENGTH(CD)

TS EN 29073-3

kg / 5cm

10

-

-

TENSILE ELONGATION(CD)

TS EN 29073-3

%

-

-

-

TENSILE STRENGTH(MD)

TS EN 29073-3

kg / 5cm

10

-

-

TENSILE ELONGATION(MD)

TS EN 29073-3

%

-

-

-

TEARING STRENGTH(CD)

TS EN ISO 9073 -

kg

1

-

-

TEARING STRENGTH(MD)

TS EN ISO 9073 -

kg

1

-

-

Standard Test Method for
Water Vapor Transmission

ASTM E398

gr/24 h.m²

100

130

-

PACKING